

PRODUCT DATA SHEET

Avery Dennison[®] MPI[™] 7000 Perforated Window Film 40 Series

Issued: 09/2025

Introduction

Avery Dennison MPI 7000 Perforated Window Film series consist of perforated, calendered films with a black backside for use on transparent substrates (i.e. glass). Both products available in this series consist of 160 micron gloss white vinyl, with 1.5 mm perforation and 40% of open area.

After printing this film allows the full graphic to be seen on one side but still allows viewing through the window from the other side.

Conversion

Avery Dennison Perforated Window Films are suitable for use on a variety of super-wide format inkjet printers using solvent, eco-/mild solvent, latex or UV-curable ink on flat surfaces only.

To enhance colour and protect the image against UV radiation and abrasion, Avery Dennison MPI 7000 PWF series is recommended to be overlaminated with Avery Dennison DOL 4000 or SL 4510. Please consult Avery Dennison Technical Bulletin 5.12 for detailed information on conversion techniques.



Face Film

MPI 7201 PWF 40: 160 micron gloss white calendered vinyl, black reverse side, 1.5 mm perforation, 40% open area

MPI 7301 PWF 40: 160 micron gloss white calendered vinyl, black reverse side, 1.5 mm perforation, 40% open area



Adhesive

Removable, transparent, acrylic based



Backing

140 g/m² PE coated liner + 55 g/m² perforated paper



Durability

MPI 7201 PWF 40: 3 years

MPI 7301 PWF 40: 1 year



Shelf Life

2 years

Recommendations

- » All types of one way vision graphics on buildings, glass panels and glass doors
- » Continuous, uninterrupted vehicle graphics covering painted and window areas
- » Colorful graphics on windows that still provide sufficient interior daylight

Features

- » High-impact promotions for passers-by
- » Good privacy inside, with a clear view of the outside
- » Fire certification available
- » Long-term durability with ICS performance guarantee
- » Controls glare, UV and solar heat

Physical Characteristics

	Test method ¹	Results
Product		
Caliper, facefilm (micron)	ISO 534	160
Caliper, facefilm + adhesive (micron)	ISO 534	185
Dimensional stability (mm max.)		
MPI 7201 PWF 40	FINAT FTM 14	0.3
MPI 7301 PWF 40	FINAT FTM 14	0.6
Shelf life (years)	Stored at 22° C/50-55 % RH	1
Durability²(years)		
MPI 7201 PWF 40	Vertical exposure, unprocessed	3
MPI 7301 PWF 40	Vertical exposure, unprocessed	1
Fire classification rating		
MPI 7201 PWF 40	EN13501-1	B-s1, d0
MPI 7301 PWF 40	EN13501-1	B-s2, d0
Adhesive		
MPI 7201 PWF 40		
Adhesion, initial (N/m)	FINAT FTM-1, stainless steel	200
Adhesion, after 24 hours (N/m)	FINAT FTM-1, stainless steel	240
MPI 7301 PWF 40		
Adhesion, initial (N/m)	FINAT FTM-1, stainless steel	180
Adhesion, after 24 hours (N/m)	FINAT FTM-1, stainless steel	240
Temperature range		
Application temperature (Minimum: °C)		10
Service temperature (°C to +°C)		-15 - +60
Chemical properties²		
Chemical resistance	Mild acids	No effect
Solvent resistance	Mild alkalis	No effect
Solvent resistance	Applied to aluminium	No effect exposed to: oils, greases, aliphatic solvents, motor oils, heptane, kerosene and JP-4 fuel.

Important

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

1) Test methods: More information about our test methods can be found on our website.

2) Prolonged immersion in gasoline and similar fluids is not recommended.

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.

Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

© 2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.